DX0518152C

№. DX051320-2018B

CMA 180021113460

中国认可
国际互认
检测
TESTING
CNAS L1177

(2018)国认监认字(571)号

检 验 报 告

TEST REPORT

SAMPLE: Metal Glass Magnesium Rock Wool Sangwich Panel

MANUFACTURER: Shandong Wiskind Steel Building Stock Cl.,Ltd

CLIENT: Qingdao TGOOD Electric Co.,Ltd

TEXT KIND: Entrust

国家消防及阻燃产品质量监督检验中心(山东)

National Supervision and Inspection Center for Fire and Flame-retardant Product Quality (Shandong)

WISKIND万事达

No.DX051320-2018B

National Supervision and Inspection Center for Fire and Flame-retardant Product Quality(Shandong)

Test Report

Sample	Metal Glass Magnesium Rock Wool Sangwich Panel	**Test Kind**	Entrust
Client	Qingdao TGOOD Electric Co.,Ltd	**Model, Type**	/
Manufacturer	Shandong Wiskind Steel Building Stock Cl.,Ltd	**Grade**	/
Address of Client	No.336 Songling Rd,Laoshan District,Co.,Ltd	**Brand**	Wiskind
Project	/	**Sampling Date**	/
Sampling Location	/	**Send/Sampling Porsonnel**	Jianlong Wei
Sample Batch	/	**Receipt Date**	2018-04-25
Sample Quantity	One piece(1200mm×600mm)	**Producing Date**	2018-04-20
Sample Description	Intact (two layer PGI：0.5mm，two layer glass magnesium:5mm,rock wool core:89mm)	**Batch No.**	M0011804070012
Environmental for Test	T:23℃ HR:/% atm:/Kpa	**Test Date**	2018-05-08
Test Standard	GB/T 9978.1-2008		
Test Item	1、Fire Resistance:120min		
Test Conclusion	Samples follow the standards GB/T 9978.1-2008 teste,Fire and heat insulation:120min,Fire resistance:120min. （Seal of Testing Laboratory）		
Note	1、 The test report contains the cover and continuation sheet ,"/"means no content. 2、 Testing address: No.16288, Shiji Road, Zhangqiu, Shandong, China. 3、 Pictures enclosed in the attachments. 4、 The sample name and production information are confirmed by the Client. 5、 Website for the report verification:www.sdzjy.com.cn/internet service/report verification system.		

Approved by: **Audited by:** **Tested by:**

Date of issue: 2018-05-10 **Date of issue: 2018-05-10** **Date of issue: 2018-05-10**

National Supervision and Inspection Center for Fire and Flame-retardant Product Quality(Shandong)

Test Report (Continuation sheet)

Number	Test Item	Unit Symbol	Technical Requirements	Test Results	Monomial Verdict
1	Fire Resistance	/	/	Fire and heat insulation:120min Fire Resistance:120min	/
Note	Samples description: Samples dimension:600mm×1200mm. Samples structure(exposed surface to unexposed surface):0.5mm color coated galvanized steel、5mm glass magnesium、89mm rock wool 5mm glass magnesium 0.5mm color coated galvanized steel.Above information offered by the consignor.				

The following blank

WISKIND万事达

Attachment: No.DX051320-2018B

National Supervision and Inspection Center for Fire and Flame-retardant Product Quality(Shandong)

Test Report Attach Pictures



Pictures1:situation of the specimen structure before the fire resistance test.



Pictures2:situation of the specimen structure when the fire resistance test finished.